


Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A composition comprising
- at least one epoxide adduct **A** having on average more than one epoxide group per molecule;
- at least one polymer **B** of the formula (I)



in which

Y_1 is an n-valent radical of a linear or branched polyurethane prepolymer terminated with isocyanate groups after removal of the terminal isocyanate groups;

Y_2 is a radical of an aliphatic, cycloaliphatic, aromatic or araliphatic epoxide containing a primary or secondary hydroxyl group after removal of the hydroxide and epoxide groups;

n is 2, 3 or 4;

m is 1, 2 or 3;

and has at least one aromatic structural element which is bound in the polymer chain via urethane groups;

at least one thixotropic agent **C** based on a urea derivative in a nondiffusing carrier material;

and

at least one curing agent **D** for epoxy resins which is activated by elevated temperature.

2. (Currently Amended) The composition as claimed in claim 1, ~~characterized in that~~wherein the epoxide adduct **A** is obtainable from the reaction

of at least one dicarboxylic acid and at least one diglycidyl ether;

or



of at least one bis(aminophenyl) sulfone isomer or of at least one aromatic alcohol and at least one diglycidyl ether.

3. (Currently Amended) The composition as claimed in claim 2, ~~characterized in that~~wherein the dicarboxylic acid is a dimeric fatty acid, in particular at least one dimeric C₄-C₂₀ fatty acid, and the diglycidyl ether is bisphenol A diglycidyl ether, bisphenol F diglycidyl ether or bisphenol A/F diglycidyl ether.

4. (Currently Amended) The composition as claimed in claim 2 ~~or 3~~, ~~characterized in that~~wherein the aromatic alcohol is selected from the group consisting of 2,2-bis(4-hydroxyphenyl)propane, bis(4-hydroxyphenyl)methane, bis(4-hydroxyphenyl) sulfone (= bisphenol S), hydroquinone, resorcinol, pyrocatechol, naphthohydroquinone, naphthoresorcinol, dihydroxynaphthalene, dihydroxyanthraquinone, dihydroxybiphenyl, 3,3-bis(p-hydroxyphenyl)phthalides, 5,5-bis(4-hydroxyphenyl)hexahydro-4,7-methanoindane, 4,4'-[bis(hydroxyphenyl)-1,3-phenylenebis(1-methylethylidene)] (= bisphenol M), 4,4'-[bis(hydroxyphenyl)-1,4-phenylenebis(1-methylethylidene)] (= bisphenol P) and all isomers of the abovementioned compounds, and the diglycidyl ether is bisphenol A diglycidyl ether, bisphenol F diglycidyl ether or bisphenol A/F diglycidyl ether.

5. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the polymer **B** is soluble or dispersible in epoxy
 resins.

6. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the polymer **B** is obtainable from the reaction of a
 monohydroxyepoxide of the formula (II) and of a linear or branched polyurethane prepolymer
 terminated with isocyanate groups and of the formula (III)



7. (Currently Amended) The composition as claimed in claim 6, ~~characterized in~~
~~that~~wherein, in the process for the preparation of the polyurethane prepolymer of the formula
 (III), at least one polyisocyanate, at least one, optionally substituted, polyphenol and at least
 one isocyanate-reactive polymer are used.

8. (Currently Amended) The composition as claimed in claim 7, ~~characterized in~~
~~that~~wherein the isocyanate-reactive polymer of the formula (III) is a polyol selected from the
 group consisting of the polyoxyalkylenepolyols, polyhydroxy-terminated


polybutadienepolyols, styrene/acrylonitrile-grafted polyetherpolyols, polyhydroxy-terminated acrylonitrile/butadiene copolymers, polyesterpolyols and polycarbonatepolyols.


9. (Currently Amended) The composition as claimed in claim 7 ~~or 8, characterized in that~~wherein the isocyanate-reactive polymer of the formula (III) is an α,ω -polyalkylene glycol having C₂-C₆-alkylene groups or having mixed C₂-C₆-alkylene groups, in particular a polypropylene glycol or a polybutylene glycol.

10. (Currently Amended) he composition as claimed in ~~any of claims 7-9~~claim 7, ~~characterized in that~~wherein the isocyanate-reactive polymer of the formula (III) has an equivalent weight of 600 - 6000 g/equivalent of NCO-reactive groups, in particular of 700 - 2200 g/equivalent of NCO-reactive group.

11. (Currently Amended) The composition as claimed in ~~any of claims 7-9~~claim 7, ~~characterized in that~~wherein the polyisocyanate of the formula (III) is a diisocyanate, preferably HDI, IPDI, TMDI, MDI or TDI.

12. (Currently Amended) The composition as claimed in ~~any of the preceding claims~~claim 1, ~~characterized in that~~wherein the polymer chain of the polymer **B** simultaneously has the structural elements of the formulae (IV) and (V)





in which

p is 2, 3 or 4, in particular p is 2 or 3;

q is 2, 3 or 4, in particular q is 2 or 3;

X is S, O or NH; in particular X is O;

Ar₁ is a p-valent, optionally substituted, aryl radical;

Y₃ is a q-valent radical of an isocyanate-reactive polymer after removal of the terminal amino, thiol or hydroxyl groups and

* is the linkage point to the remainder of the polymer chain.

13. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the proportion by weight of all polymers **B** of the
formula (I) is from 5 to 40% by weight, preferably from 7 to 30% by weight, based on the
weight of the total composition.

14. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the carrier material of the thixotropic agent **C** is a
blocked polyurethane prepolymer.

15. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the urea derivative in the thixotropic agent **C** is a
product of the reaction of an aromatic monomeric diisocyanate, in particular 4,4'-
diphenylmethane diisocyanate, with an aliphatic amine compound, in particular butylamine.

16. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the total proportion of the thixotropic agent **C** is 5
- 40% by weight, preferably 10 - 25% by weight, based on the weight of the total
composition.

17. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the proportion of the urea derivative is 5 - 50% by
weight, preferably 15 - 30% by weight, based on the weight of the thixotropic agent **C**.

18. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the curing agent **D** is a latent curing agent
selected from the group consisting of dicyandiamide, guanamines, guanidines and
aminoguanidines.

19. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the total proportion of the curing agent **D** is 1 -
10% by weight, preferably 2 - 8% by weight, based on the weight of the total composition.


20. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein at least one filler **E** is additionally present.

21. (Currently Amended) The composition as claimed in claim 20, ~~characterized in~~
~~that~~wherein the total proportion of the filler **E** is 5 - 30% by weight, preferably 10 - 25% by
weight, based on the weight of the total composition.

22. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein at least one reactive diluent **F** carrying epoxide
groups is additionally present.

23. (Currently Amended) The composition as claimed in ~~any of the preceding~~
~~claims~~claim 1, ~~characterized in that~~wherein the composition, after curing, has a low-
temperature fracture energy, measured according to DIN 11343, of more than 10 J at -20°C
and of more than 7 J at -40°C and preferably of more than 11 J at -20°C and of more than 9 J
at -40°C.

24. (Original) An impact strength modifier terminated with epoxide groups and of the
formula (I)



in which

Y_1 is an n-valent radical of a linear or branched polyurethane prepolymer terminated
with isocyanate groups after removal of the terminal isocyanate groups;



Y_2 is a radical of an aliphatic, cycloaliphatic, aromatic or araliphatic epoxide
containing a primary or secondary hydroxyl group after removal of the hydroxide and epoxide
groups;

n is 2, 3 or 4;

m is 1, 2 or 3;

and has at least one structural element which is bound in the polymer chain via urethane groups.

25. (Currently Amended) The impact strength modifier terminated with epoxide groups, as claimed in claim 24, ~~characterized in that~~wherein the polymer chain of the impact strength modifier simultaneously has structural elements of the formulae (IV) and (V)



in which

p is 2, 3 or 4, in particular p is 2 or 3;

q is 2, 3 or 4, in particular q is 2 or 3;

X is S, O or NH; in particular X is O;

Ar₁ is a p-valent, optionally substituted aryl radical;

Y₃ is a q-valent, optionally chain-extended, radical of an isocyanate-reactive polymer after removal of the terminal amino, thiol or hydroxyl groups and

* is the linkage point to the remainder of the polymer chain.

26. (Currently Amended) The impact strength modifier terminated with epoxide groups, as claimed in claim 24 ~~or 25, characterized in that~~wherein the impact strength modifier is obtainable from the reaction of a monohydroxyepoxide of the formula (II) with a linear or branched polyurethane prepolymer terminated with isocyanate groups and of the

formula (III), and in that at least one polyisocyanate and at least one polyphenol and at least one isocyanate-reactive polymer are used in the preparation of this polyurethane prepolymer.

27. (Currently Amended) The use of a composition as claimed in ~~any of claims 1—23~~claim 1 as a one-component adhesive.

28. (Currently Amended) The use of an impact strength modifier terminated with epoxide groups, as claimed in ~~any of claims 24—26~~claim 24, in a two-component adhesive, ~~characterized in that~~wherein this impact strength modifier is a constituent of the first component and at least one polyamine or at least one polymercaptan is a constituent of the second component.

29. (Currently Amended) The use as claimed in claim 27 ~~or 28, characterized in that~~wherein the adhesive is used for the adhesive bonding of heat-stable materials, in particular of metals.

30. (Currently Amended) The use as claimed in ~~any of claims 27 to 29~~claim 27, ~~characterized in that~~wherein the adhesive is used as a body-shell construction adhesive in automotive construction.

31. (Currently Amended) A method for the adhesive bonding of heat-stable materials, in particular of metals, ~~characterized in that~~wherein these materials are brought into contact with a composition as claimed in ~~any of claims 1—23~~claim 1 and comprises a subsequent step of curing at a temperature of 100 - 220°C, preferably 120 - 200°C.